IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re application of: Confirmation No.: 2978

HONG et al. Art Unit: 1792

Application No.: 10/767,854 Examiner: Ngampa, Briget P.

Filed: January 30, 2004 Atty. Docket: 2236.0070000/JUK/SMW

For: Oxidation Protective Coating Method for Carbon/Carbon Composites

Declaration of Soon Hyung Hong, Yang Ho Bae, Ji Young Song and Hee Yeoun Kim Under 37 C.F.R. § 1.132

Attn: Mail Stop Amendment

Commissioner for Patents PO Box 1450 Alexandria, VA 22313-1450

Sir:

The undersigned Soon Hyung Hong, Yang Ho Bae, Ji Young Song and Hee Yeoun Kim declare and state as follows:

- We are co-inventors of the invention described in one or more of the pending claims of the captioned application.
- It is our understanding that claim 5 of the captioned application was rejected by
 the Examiner in the Office Action of February 11, 2008, over Galasso et al. (U.S.
 Pat. No. 4,425,407), Booth et al. (U.S. Pat. No. 5,330,789), Holko et al. (U.S. Pat.
 No. 5,021,107) and Hanzawa et al. (U.S. Pub. No. 2001/051,258).
- It is our understanding that claim 5 as rejected by the Examiner recited: "The method of claim 1, wherein the heat-treating in (b) is performed at a temperature

of about 1400 °C to about 1600 °C under a pressure of about 10 mTorr to about

- 4. It is our understanding that the features of claim 5 have been incorporated into amended claim 1 in the present Amendment and Reply, and that claim 5 has been cancelled. Amended claim 1 recites: "A method of making an oxidation protective coating for a carbon/carbon composite, the method comprising:
 - spraying a mixture comprising a vehicle liquid and Si powder on the carbon/carbon composite and drying the mixture to remove the vehicle liquid:
 - (b) heat-treating to allow the carbon/carbon composite to be impregnated with the Si, thereby forming an SiC layer and an Si layer, wherein the heat-treating is performed at a temperature of 1400°C to about 1600°C under a pressure of about 10 mTorr to about 1000 mTorr; and
 - (c) oxidizing the Si layer to form an SiO2 film.
- 5. The temperature range of the heat treating in (b) is critical, and the considerations for the heat treating include (1) economic cost considerations, and (2) functional considerations, including the complete and uniform infiltration of the Si on the carbon/carbon composites.
- To minimize the economic costs associated with heat treating, we have found that
 high temperature processing above 1600 °C is not necessary. This point was
 identified in the captioned application at paragraph [0044].

- 7. Fluidity of Si powder is important in the process of Si infiltration. Solid state Si powder does not have good fluidity, making movement of the Si into carbon/carbon composite pores difficult. Also, in order to be coated, the carbon/carbon composite substrate and Si should react together. Reactions between the carbon/carbon composite and Si are minimal if Si is in a solid state.
- Fluidity of Si is insufficient at 1380 °C, resulting in an imperfect coating as shown in Fig. 1.



Fig.1. When infiltration is performed at a low temperature (1380 °C), carbon fiber shows and pores or cracks are not coated perfectly.

9. The known melting temperature of Si is 1412 °C. To increase the diffusion speed of the Si into the pores, the temperature should be increased near to or higher than the melting point of Si. In order to investigate temperatures which result in an effective fluidity of Si, heat treating temperatures between 1400 °C \sim 1600 °C were attempted.

-4-

When the heat treating was performed near the melting point (1412 °C), Si
fluidity increases as shown in Fig. 2 and the Si adheres to the carbon/carbon
composite.




Fig. 2. Carbon/carbon composite Si-infiltrated at 1412 °C (melting point).

However, Fig. 2 demonstrates that while Si coats the composite in some areas, other areas contain pores. The pores result from the insufficient fluidity of Si, indicating that the heat treating should occur at a temperature at or above the melting point.

 When the heat treating temperature increased to 1425°C, the carbon/carbon composite was coated uniformly as in Fig. 3.




Fig.3. Carbon/carbon composite Si-infiltrated at 1425 °C

The uniformly coated Si on the carbon/carbon substrate improved oxidation resistance.

12. The data presented herein demonstrates the critical nature of heat treating the Si-coated carbon/carbon composite to impregnate the initial coating layer and cracks in the initial coating later with Si.

 I have read and understand 37 C.F.R. § 	10.18(b) and (c).
--	----------------	-----

2008. 5.30 Date	foonh. Hong
Date	Soon Hyung Hong
Date	Yang Ho Bae
Date	Ji Young Song
Date	Hee Yeoun Kim

822698_2.DOC

-6-

HONG et al. Appl. No. 10/767,854

13. I have read and understand 37 C.F.R. § 10.18(b) and (c).

Date	Soon Hyung Hong	
2008 5.30.	Karg Ho Bae	
Date	/ ang Ho Bae	
Date	Ji Young Song	
Date	Hee Yeoun Kim	

822698_2.DOC

 a;

13.	I have read and understand 37 C.	P P K 10 19/h) and (a)
13.	I have read and understand 57 Ca	r.n. g 10.10(0) and (0).

Date	Soon Hyung Hong	
Date	Yang Ho Bae	
2008. 6.3	Ji Young Song	
Date	Hee Youn Kim	***

\$22698_2.DOC

Date	Soon Hyung Hong
Date	Yang Ho Bae
Date	Ji Young Song
May 30, 2008	Hee Yeoun Kim

822698_2.DOC